

Opti-Clear Specifications

	TEST	PERFORMANCE	STANDARD
Dimensions:	53.5" by 110"		(approx. +- .5")
Thickness:	030, .040, .060		+- .004
Specific Gravity:	ASTM D-792	1.2832	
Abrasion Resistance: (Wyzenbeek #8 Cotton Duck / 4 lb tension and 3 lb compression force)	ASTM D-3597 / ASTM D-4157	no evidence of surface scratches	10,000 cycles
Tensile Strength:	ASTM D-882	3943.7	3100-3700
Luminous Transmission	ASTM D-1003	88.8%	Min. 70%
Cold Flex:	FLTM59-5	-10F	Min. -10F
Cold Impact:		OF	
Elongation:	ASTM D-882	241.6	190-230
100% Modulus:	ASTM D-882	3007.4	2550-2950
Haze:	ASTM D-1003	0.236	> 0.9
Graves Tear:	ASTM D-882	636.4 lbs/in.	550-590
Flammability:	FMVSS-302 / CMVSS-302		No burn rate
Weatherability:	ASTM G-53		No change 1000 hrs.

CoverMyTractor.com